

January 2011



RUBBER & PLASTICS CORP.

# PHYSICAL PROPERTIES CHART

## DURAFOAM™ P391SHD

TYPICAL PHYSICAL PROPERTIES	DURAFOAM™ P391SHD
POLYMER	100% EPDM
COLOR	BLACK
ASTM D-1056-00 CLASSIFICATION	2A3
25% COMPRESSION RESISTANCE (psi)	9 TO 13
B2 - 50% COMPRESSION SET (%) max.	25
C1 – OZONE EXPOSURE, ASTM-D- 1171, METH. A	PASS
F2 – LOW TEMPERATURE RESISTANCE, -67° F	PASS
M-COMBUSTION CHARACTERISTICS, TEST METHOD D5132 100 min/max (4 in./min, max)	PASS
DENSITY (lbs/ft <sup>3</sup> ) approx	15
WATER ABSORPTION (lbs/ft. <sup>2</sup> )	.01 max.
WATER ABSORPTION, By Weight ASTM-D-1056 (max)	1% max.
TENSILE (psi)	150 min.
ELONGATION (%)	200% min.
FLAMMABILITY – FMVSS302	PASS
LOW TEMPERATURE FLEXIBILITY	-80° F
OZONE 20% STRESS – 72 hrs. @100 PPHM GM 4486P, ASTM-D-1171-94, ASTM-D-1149-91	NO CRACKS
WEATHERING	EXCELLENT
ULTRAVIOLET	EXCELLENT
STAINING – RES.30 ST 133 Issue No. 2 (Europe)	NO STAINING

**DISCLAIMER:** To the extent that the above product information is derived from sources other than Monmouth Rubber, Monmouth Rubber is substantially, if not wholly, relying upon the other source(s) to provide accurate information. Information provided as a result of Monmouth Rubber's own technical analysis and testing is accurate to the extent of our knowledge and ability, using effective standardized methods and procedures. Each user of these products, or information, should perform their own tests to determine the safety, fitness and suitability of the products, or combination of products, for any foreseeable purposes, applications and uses by the user and by any third party to which the user may convey the products. Since Monmouth Rubber cannot control the end use of this product, Monmouth Rubber does not guarantee that the user will obtain the same results as published in this document. The data and information is provided as a technical service, and the data and information is subject to change without notice. When considering the above product as a competitive equivalent material, please keep in mind that some materials have unique physicals that are not part of the recognized industry specifications and standards. Therefore, customer sample evaluation and approval of any substitution is suggested. Monmouth Rubber will supply free of charge evaluation & testing of its materials to assist customers in their evaluation. For technical evaluation and support, please contact John M. Bonforte, Sr., Ext. 12, or email: [johnsr@monmouthrubber.com](mailto:johnsr@monmouthrubber.com).



**ISO CERTIFIED  
TO 9001:2008**

### Have a Technical Question?

“Ask John” is Monmouth’s global technical support service. It is **FREE** and brings real value to your company. It allows Monmouth’s customers and visitors to have a 24/7 Technical Library & Test lab, absolutely **FREE**. Have a technical question or problem? Just email [johnsr@monmouthrubber.com](mailto:johnsr@monmouthrubber.com), or call 1-732-229-3444 Ext 12 and “Ask John”.

## PHYSICAL AND SHOCK ATTENUATION TEST LABORATORY

**75 LONG BRANCH AVENUE, LONG BRANCH, NJ 07740**

**PHONE: 888-FOAM-888**

**FAX: 800-375-1962**

**Email: [sales@monmouthrubber.com](mailto:sales@monmouthrubber.com)**

**Internet: [www.rubberplastics.com](http://www.rubberplastics.com)**