



November 2010

PHYSICAL PROPERTIES CHART
BONDAFLEX B33CS SPONGE

TYPICAL PHYSICAL PROPERTIES

POLYMER	NEOPRENE BLEND
COLOR	BLACK
DENSITY, Approx. (lbs/cu.ft)	30PCF MIN.
RECOVERY	90% MIN.
COMPRESSION	50PSI TO 1500PSI
WEATHERING	NO DISINTEGRATION
EXTRUSION	LESS THAN 0.25"
SPECIFICATION	HH-F-341-F-TY 2-CLASS A
SPECIFICATION	AASHO-M-153-70, TY 1
SPECIFICATION	ASTM-D-1752, TY 1
STOCK NUMBER	B33CS - BLACK

DISCLAIMER: To the extent that the above product information is derived from sources other than Monmouth Rubber, Monmouth Rubber is substantially, if not wholly, relying upon the other source(s) to provide accurate information. Information provided as a result of Monmouth Rubber's own technical analysis and testing is accurate to the extent of our knowledge and ability, using effective standardized methods and procedures. Each user of these products, or information, should perform their own tests to determine the safety, fitness and suitability of the products, or combination of products, for any foreseeable purposes, applications and uses by the user and by any third party to which the user may convey the products. Since Monmouth Rubber cannot control the end use of this product, Monmouth Rubber does not guarantee that the user will obtain the same results as published in this document. The data and information is provided as a technical service, and the data and information is subject to change without notice. When considering the above product as a competitive equivalent material, please keep in mind that some materials have unique physicals that are not part of the recognized industry specifications and standards. Therefore, customer sample evaluation and approval of any substitution is suggested. Monmouth Rubber will supply free of charge evaluation & testing of its materials to assist customers in their evaluation. For technical evaluation and support, please contact John M. Bonforte, Sr., Ext. 12, or email: johnsr@monmouthrubber.com.



ISO CERTIFIED 9001:2008
CERTIFICATE #US08/5033

Have a Technical Question?

"Ask John" is Monmouth's global technical support service. It is **FREE** and brings real value to your company. It allows Monmouth's customers and visitors to have a 24/7 Technical Library & Test lab, absolutely **FREE**.

Have a technical question or problem?
Just email johnsr@monmouthrubber.com,
or call 1-732-229-3444 Ext 12
and **"Ask John"**.

PHYSICAL AND SHOCK ATTENUATION TEST LABORATORY

75 LONG BRANCH AVENUE, LONG BRANCH, NJ 07740

PHONE 888-FOAM-888

FAX 800-375-1962

E-mail sales@monmouthrubber.com

Internet <http://www.rubberplastics.com>